

### 1. PRODUCT NAME

#### Dynaflex® Acrylic Resurfacer Sandmix

### 2. MANUFACTURER

Neyra Industries, Inc.  
10700 Evendale Drive  
Cincinnati, Ohio 45241

Phone: 513-733-1000  
Toll Free: 800-543-7077  
Fax: 513-733-3989  
Email: info@neyra.com  
Website: www.neyra.com

- **Fast Drying:** Allows multiple coats in one working day.
- **Specially Formulated:** 100% compatible with Dynaflex Acrylic Color Coating.
- **Non-Scuffing:** 100% synthetic will not mark tennis balls or shoes.
- **Easy to Use:** Non-settling, easy to mix.
- **Versatile:** May be used as final coat if black non-fading surface is desired.

### 3. PRODUCT DESCRIPTION

Dynaflex Acrylic Resurfacer Sandmix is a pigmented concentrated acrylic textured coating system. This silica-fortified coating will provide a smooth, even-textured and flexible surface.

#### Packaging:

Packaged in 5 gallon pails, 30 gallon kegs, and 55 gallon steel drums.

#### Color:

Stock standard color is black. Dynaflex Resurfacer Sandmix without pigment, neutral and gray, is also available by special order.

#### Basic Uses:

Dynaflex Acrylic Resurfacer Sandmix is recommended for smoothing and filling texture on asphalt surfaces prior to application of Dynaflex color coating. In addition it can be used as a finish for any asphalt or concrete surface where a durable black surface is desired.

#### Composition:

Dynaflex Acrylic Resurfacer Sandmix is a blend of binders, pigment, surfactants and rheology agents in a water-based emulsion. Premium quality 100% acrylic polymers give Dynaflex Acrylic Resurfacer Sandmix its tough, long wearing character.

The surfactants blended into Dynaflex Acrylic Resurfacer Sandmix create a superior bond between the product and the pavement surface.

The rheological agents allow the emulsion to maintain long shelf life and an excellent non-settling character.

#### Limitations:

In the liquid state, Dynaflex Acrylic Resurfacer Sandmix must be protected from freezing and rain. Do not store in direct sunlight or where temperature exceeds 120°F.

### 4. INSTALLATION

#### Preparatory Work:

The surface must be structurally sound, surface cured, and free from all loose or foreign matter prior to the application of Dynaflex Acrylic Resurfacer Sandmix.

An asphalt recreational surface should be checked for irregularities or depressions deeper than 1/8" (birdbaths). Fill to level of surrounding surface with hot mix asphalt or Dynabinder Quick Patch Binder (Product Data Sheet 261) prior to the application of Dynaflex Acrylic Resurfacer Sandmix.

On a concrete recreational surface, the finish should be wood float or light broom, not steel troweled. The surface should be checked for depressions deeper than 1/8". Fill to level of surrounding surface with Dynabinder Quick Patch Binder prior to the application of Dynaflex Acrylic Resurfacer Sandmix.

In addition, new concrete surfaces should be lightly abraded or lightly acid-etched and then primed with

DynaPrime Primer (Product Data Sheet 159) prior to the application of Dynaflex Acrylic Resurfacer Sandmix.

**Note:** In all cases a vapor barrier beneath concrete surface is strongly recommended.

#### Methods:

Dynaflex Acrylic Resurfacer Sandmix can be applied by squeegee or brush. On new tennis or basketball courts, squeegee application is the recommended method.

#### Mix Design:

As supplied, Dynaflex Acrylic Resurfacer Sandmix is a highly concentrated material intended to be mixed with water to form a ready-to-use pavement resurfacer and finish coat. Per 30 gallon keg of Dynaflex Acrylic Resurfacer Sandmix, add 14 gallons of water.

Per 30 gallons of Dynaflex AR Sandmix

Water	Yield
14 gal.	44 gal.

#### Application:

For use over asphalt or concrete pavements, the following application procedures are recommended for best results.

Each application of the properly mixed, ready-to-use material will cover at a rate of 6 to 9 sq. yds. per gallon. Coverage rates can vary with the age, texture and porosity of the pavement

to be sealed and with the method of application.

Application must be made when ambient and pavement temperatures are above 50°F. Night time application is not recommended. It is recommended that the area over which the application is made be open to use only after trial shows it to be cured sufficiently.

Under good drying conditions, with the sun and breeze at 70°F or higher, Dynaflex Acrylic Resurfacer Sandmix will dry in 1 to 4 hours depending on the surface condition and the thickness of the applied coating.

As a finish coat, allow 2 to 4 hours of good drying before recoating and 48 hours before play.

#### **Precautions:**

Liquid Dynaflex Acrylic Resurfacer Sandmix must be protected at all times from freezing. Keep out of reach of children. Container should be closed when not in use. Avoid breathing vapor or contact with skin or eyes. Consult specific Neyra material safety data sheet before use.

New asphalt should be allowed to cure for a minimum of 30 days prior to application and must not exhibit ribboning, crawling, nor show oil rings when 1 gallon of clean water is poured onto the surface.

New concrete pavement should be allowed to cure for a minimum of 30 days prior to application.

#### **5. MAINTENANCE**

Proper care of the finished surface will maintain the attractive appearance and prolong the service of the Dynaflex coating system. Keeping leaves and other foreign matter off the surface and occasional flushing with clean cold water will achieve good results.

#### **6. TECHNICAL DATA**

##### ***Adhesion and Resistance to Water***

The cured coating exhibits no penetration, blistering, loss of adhesion, nor tendency to re-emulsify after immersion for 24 hours. Complete sampling and test procedures are available upon request.

##### ***Environmental Considerations:***

Dynaflex Acrylic Resurfacer Sandmix is considered non-hazardous when tested according to the EPA's TCLP (Toxicity Characteristic Leaching Procedure). Dynaflex Acrylic Resurfacer Sandmix is a water-based material containing less than 101 g/L (0.84 lbs./gal.) VOC content.

#### **7. TECHNICAL SERVICES**

C.S.I. formatted application specifications, material safety data sheets, special project submittals, product and application recommendations as well as assistance with special situations and field service are available.

#### **8. WARRANTY**

The above specifications on product usage are believed to be true and accurate. Neyra Industries, Inc. guarantees that all materials manufactured comply with quality standards as described in the product data sheets. Because the application, handling, weather, workmanship and equipment are beyond the control of this manufacturer, only the quality of the products as shipped is guaranteed. In no case will the liability of Neyra Industries, Inc. exceed the purchase price of the shipped materials.

#### **9. ADDITIONAL INFORMATION**

Neyra Industries, Inc. manufactures a full line of recreational surface and asphalt pavement maintenance products as well as application equipment sold and distributed nationally at our plants and through distributors and contractors. To find the supplier most convenient to you, please contact us.

## **NEYRA**

Neyra Industries, Inc.  
10700 Evendale Drive  
Cincinnati, Ohio 45241

Phone: 513-733-1000  
Toll Free: 800-543-7077  
Fax: 513-733-3989  
Email: [info@neyra.com](mailto:info@neyra.com)  
Website: [www.neyra.com](http://www.neyra.com)